



火気厳禁、業務用

# スマイル UP シンナー #100

## Smile Up Thinner #100

NET 16L



危険情報及び法規関連情報

危険有害情報：

- 引火性の高い液体及び蒸気
- 飲み込むと有害のおそれ
- 皮膚刺激
- 強い眼刺激
- 生殖能又は胎児への悪影響のおそれ
- 呼吸器への刺激のおそれ、眠気およびめまいのおそれ
- 長期または反復暴露による臓器の障害
- 飲み込み、気道に侵入すると有害のおそれ
- 水生生物に有害
- 長期的影響により水生生物に有害のおそれ

消防法：危険物第4類第1石油類危険等級II  
有機溶剤中毒予防規則：第2種有機溶剤  
指針番号128、国連番号1263

労働安全衛生法による表示  
キシレン

<Using Method>

### 1、Standard coating process

No.	Process	Material Mixing ratio	Temperature: 27°C		
			Application Method	Application quantity	Drying time
1	Surface preparation	Remove dirt and extraneous matter carefully not to hurt wood part. Oil should be wiped off with solvents, and wood resin be scrape off or be wiped off with solvents after using an electric branding iron. Holes should be filled with a wood putty.			
2	Wood sanding	Sand paper No. 180-240			
3	Coloring	Smile UP Filler 100 Smile UP Thinner #100 30-50	Brushing & wiping with clothes	30-50g/m <sup>2</sup>	2 hours and over
4	Undercoat (once or twice)	Smile UP Sealer A liquid 100 Smile UP Sealer B liquid 50 Smile UP Thinner #200 60-90	Spraying	80-100	2 hours and over
5	Sanding	Sand paper No. 320-400			
6	Topcoat	Smile UP Top A liquid each%80 Smile UP Top B liquid20 Smile UP Thinner #200 0-60	Spraying	80-100	1 day and over

2、 Please use for thinner of SmileUp Filler

3、 Please use for thinner of Urethane paints, "Smile up" series and LacquerKongou as retarder.  
Adding 1~5% in paints.

## 大谷塗料株式会社

住所、電話番号

製品管理番号